Asbestos Packing with Graphite Impregnation

Code: RGSP806



Description

Braided from high quality asbestos fiber impregnated with graphite and oil, it has good elasticity and good sliding properties. It can be reinforced with metal wire.

RGSP806S -- Glass Fiber Packing reinforced with SS Wire



Asbestos Packing with Graphite Impregnation Item no.: RGSP806

* Low maintenance, easy to control

* Excellent capabilities of high strength and high temperature resistance * Economical packing

Typical Application

- * Universal packing, for rotary, reciprocating pumps, in ship building and domestic fresh water pumps.
- * Suited for chemical neutral and resistant to water, steam, hot air, oils, etc.

Technical Data

Material		Asbestos Fiber and Graphite
Temperature Range		-100 up to +450 oC
Process	Rotating	20 bar
	Reciprocating	40 bar
	Static	80 bar
Shaft Speed		10 m/s
PH		3~12
Density		0.75~1.5 g/cm3