
# Mineral Fiber Rubber Sheet Reinforced with Wire Mesh

Code: RGSB702



## **Description**

Mineral Fiber Rubber Sheet Reinforced with Metal Mesh is made of good Mineral fiber rubber with steel wire inserted and compound heating and compression molding. Normal within graphite coated both surface.



Item no.: RGSB702

Mineral Fiber Rubber Sheet Reinforced with Wire Mesh

Item no.: RGSB702

- \* Economical sheet
- \* Wide range of pressure and temperature

## **Typical Application**

- \* Used for equipment in water, steam, etc.
- \* Used as sealing material in the joint of pipeline

#### **Technical Data**

| Mineral Fiber Rubber Sheet Reinforced with Metal Mesh |                         |                        |                        |
|---|-------------------------|------------------------|------------------------|
| GB/T539-1995  |                         |                        |                        |
| Item  | B70245                  | B70235                 | B70225                 |
| Tensile Strength ≥ Mpa                                | 21.0                    | 16.0                   | 11.0                   |
| Aging coefficient ≥ Mpa                               | 0.9                     |                        |                        |
| Burning loss ≤ %                                      | 27                      | 29                     |                        |
| Density g/cm3   | 1.6~2.0                 |                        |                        |
| Compressibility %                                     | 12+/-5                  |                        |                        |
| Rebound degree  | 42                      | 40                     |                        |
| Pliability  | No crack                |                        |                        |
| Stress relaxation ≤                                   | 50                      |                        |                        |
| Steam Airetightness                                   | With the temperature of | With the temperature   | With the temperature   |
|   | 440~450oC and the       | of 340~350oC and the   | of 240~250oC and the   |
|   | pressure of 13~14Mpa,   | pressure of 9~10Mpa,   | pressure of 7~8Mpa,    |
|   | keep for 30min without  | keep for 30min without | keep for 30min without |
|   | puncture                | puncture               | puncture               |

#### **Dimensions**

4100x1500x(0.5~6.0)mm, 2000x1500x(0.5~6.0)mm 1500x1360x(0.5~6.0)mm, 3810x1270x(0.5~6.0)mm 1270x1270x(0.5~6.0)mm, 1500x1500x(0.5~6.0)mm

Copyright © 2014 RGS
Rubber & Gasket Supplies Co., Ltd
Rm 1811, Huaxia Media Buliding
No.53N. Avenue, Yantai, Shandong 264000 China
sales@rgs-asia.com